

DISPARLON® NS-5500

Liquid Thixotrope for Improved Pigment Orientation & Suspension

DISPARLON NS-5500 is a post-addable hybrid type thixotropic agent for use in solventborne systems.

- ✔ Excellent orientation of metallic, pearlescent and flattening silica
- ✔ Excellent pigment suspension
- ✔ Ease to use (pourable)
- ✔ Easy incorporation by post addition



Performance

Aluminum Metallic (Alpaste 7620NS [TOYO])

Matte 2K Polyurethane

Anti-settling Test: 7 Days
(Viscosity: 17 sec #4 Ford)

Pigment Orientation

Silica Orientation



Hard Pack


Blank

5% NS-5500



Blank

5% NS-5500



Blank

5% NS-5500

Applications

Satin/Semigloss
Wood Coatings



Aerosol
Coatings



Metal/Plastic
Parts



Auto OEM
& Refinish



Typical Properties

Appearance	White liquid
% Active	7
Solvent	Aromatic 100, Ethanol, IPA

Typical Use Levels

3-8% based on total formula weight

Incorporation

Post add with good mixing

Contact

Global Headquarters
Tech. Service, R&D,
and Sales

King Industries, Inc.
1 Science Rd.
Norwalk, CT 06852

Phone: 1-203-866-5551
www.kingindustries.com



The conditions of your use and application of our products, technical assistance and information (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. Such testing has not necessarily been done by King Industries, Inc. ("King"). The facts, recommendations and suggestions herein stated are believed to be reliable; however, no guaranty or warranty of their accuracy is made. EXCEPT AS STATED, THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS OR OTHERWISE. KING SHALL NOT BE HELD LIABLE FOR SPECIAL, INCIDENTAL, CONSEQUENTIAL OR EXEMPLARY DAMAGES. Any statement inconsistent herewith is not authorized and shall not bind King. Nothing herein shall be construed as a recommendation to use any product(s) in conflict with patents covering any material or its use. No license is implied or granted under the claims of any patent. Sales or use of all products are pursuant to Standard Terms and Conditions stated in King sales documents.